

O8100 Lascaux® Acrylic Glue 303 HV

Technical Data:

Thermoplastic copolymeric butyl-methacrylate-dispersion, thickened with acrylic ester acid. The pH-value is stabilized at 8-9 and is treated with preservatives.

Film-formation:

Minimal film-formation temperature:	approx. 0°C
Glass transition temperature:	approx. - 35°C
Elongation at break:	> 1000 %
Minimal sealing temperature:	approx. 50°C
Dry film:	sticky

Solubility:

- dilutable with water, after drying: water-insoluble
- permanently soluble in acetone, alcohols, toluene, xylene.
- slightly soluble in white spirit.

Application:

For light and ageing-resistant, non-cross-linking agglutination such as re-lining, marouflage, lamination, collages etc. Applicable as wet or reactive dry technique, on absorbent and non-absorbent grounds such as paper and cardboard, textiles, wood and fibreboards, polyester boards, gypsum plaster and concrete, glass and acrylic glass, aluminium, etc.

Lascaux® Acrylic glue 303 HV is extremely elastic. The dry film stays permanently sticky. It is suitable for warm sealing when re-lining. May be used as contact adhesive.

Storage:

Store in tightly closed containers at 5 – 25°C.